

TEST REPORT

CLIENT:

Company:	Sunflex Recycling Pvt. Ltd	Report Number:	69503B				
Address:	Plot No 274/4, Shital Estate B/H Satyamev Complex	Lab Test Number:	2880-1110				
	Opp.Gujarat High Court, S. G. Highway, Sola	Test Completion Date:	12/22/2016				
	Ahmedabad-380060, Gujarat India	Report Date:	12/22/2016				
		Page:	1 of 1				
Requested By:	Milind Patel						

TEST MATERIAL:

Material Type:	Rubber Surfacing			Date Received:		12/15/201	6		
Material Condition:	EXCELLENT:	XXX	GOOD:	POOR:			REJE(CTED:	
Style Name: Interlocking Rubber Tiles		Thickness:		15mm					

TESTING METHODS REQUESTED:

TESTING METHODS REQUESTED.					
Testing Services Inc. was instructed by the client to test for the following					
Standard: ASTM E303-93(2013) Test Method:			Standard Test Method for Measuring Surface Frictional Properties Using the British Pendulum Tester		

SAMPLING PLAN:

Sampling Date: 12/15/2016

- Specimen sampling is performed in the sampling department at TSI.
- The sampling size of specimens is determined by the test method requirements.
- In the event a specific sampling size is not called for, a determination will be made based on previous testing experience, and approved for use by an authorized manager.
- All samples are subjected to the outside environmental conditions of temperature and relative humidly.
- Sample requiring pre-determined exposure to specified environmental conditions based on a specific test method, take place in the departments in which they are tested

DEVIATION FROM TEST METHOD:

ᆫ	DEVIATION FROM TEST METHOD.							
State reason for any Deviation from, Additions to, or Exclusions From Test Method.								
	None							

TEST SHIMMARY.

TEST SOMMANT.							
TEST METHOD	TEST DESCRIPTION	TEST RESULT					
ASTM E303-93(2013)	Skid Resistance Average of both Directions 43.5 BI		43.5 BPN				

- Under NVLAP guidelines, TSI is to report any outsourcing of testing to another laboratory facility.
- > In the above testing, all of tests were outsourced to: Future Labs, LLC. Their accreditations are on file and available upon request.

Uncertainty:

We undertake all assignments for our clients on a best effort basis. Our findings and judgments are based on the information to us using the latest test methods available.

TSI can only ensure the test results for the specific items tested.

Unless otherwise noted in the deviations sections of this report, all tests performed are in compliance with stated test method.

Test Report Approval:

Erle Miles, III Lab Director, Testing Services Inc

Form:	Rev:	Revision Date:	Page 1 of 1	
Release Date:	Control Type: Electronic – Expires 24 hours after this date: Dec. 22, 16			
	Printed copies are uncontrolled			