

TEST REPORT

DATE: 08-25-2026

Page 1 of 1

TEST NUMBER: 0333136

CLIENT	Sunflex Recycling Private Limited
--------	-----------------------------------

TEST METHOD CONDUCTED	ASTM D3574 Density and Compression Force Deflection, ASTM D3676 Compression Resistance, ASTM D3575 Compression Set Foam Battery
-----------------------	---

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Rubber Base

GENERAL PRINCIPLE

The samples were prepared and tested in accordance with applicable portions of test method ASTM D3574, ASTM D3676 and ASTM D3575.

TEST RESULTS

TEST DESCRIPTION	METHOD	RESULTS
Density	ASTM D3574	58.2 lbs/ft ³
Compression Resistance @ 75%	ASTM D3676	>1250.0 lbs/sq inch*
Compression Set @ 50%	ASTM D3575	5.0%
Compression Force Deflection @ 50%	ASTM D3574	402.6 lbs/sq inch

***NOTE: Exceeds machine detection limit.**

APPROVED BY: Brandon Stokes
Lab Director

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products.

This report, or the name of Professional Testing Laboratory, LLC, shall not be used under any circumstance in advertising to the general public.